

TITLE OF THE INVENTION

[0001] Process of Producing Fuel Gas for Fuel Cell

CROSS-REFERENCE TO RELATED APPLICATIONS

[0002] This is a division of co-pending application no. 10/143,108, filed May 10, 2002, now
5 abandoned, the disclosure of which is incorporated herein by reference.

BACKGROUND OF THE INVENTION

[0003] This invention relates to an autothermal reforming catalyst. This invention also
relates to a process of producing a fuel gas for a fuel cell wherein hydrocarbons and/or oxygen-
containing hydrocarbons are converted to a reformed gas which is composed principally of
10 hydrogen by an autothermal reforming reaction using such a catalyst.

[0004] A known process for producing hydrogen from hydrocarbons or oxygen-containing
hydrocarbons is an autothermal reforming method which is the combination of an oxidation reaction
and a steam reforming reaction. In this process, hydrocarbons or nitrogen-containing hydrocarbons,
steam, and oxygen or air are introduced into a reactor, and a part of the hydrocarbons or oxygen-
15 containing hydrocarbons is subjected to partial or complete combustion. While the reactor is then
heated to a predetermined temperature with the heat generated by the combustion, the remaining
hydrocarbons or oxygen-containing hydrocarbons are steam-reformed such that they are converted
to a reformed gas which is composed principally of hydrogen. While a catalyst is charged into the
reactor, it is required to have a combustion activity and a steam reforming activity.

20 [0005] Examples of such a catalyst are base metal-based catalysts such as nickel, copper, iron,
and cobalt, and noble metal-based catalysts such as platinum, rhodium, ruthenium, iridium, and
palladium.

[0006] The base metal-based catalysts are relatively prone to cause carbon precipitation. Since
in order to suppress this, it is necessary to use materials of the catalyst, i.e., hydrocarbons or oxygen-
25 containing hydrocarbons with an excess amount of steam, resulting in a condition where the
steam/carbon ratio is high, the activity is inevitably reduced.

[0007] On the other hand, since the noble metal-based catalysts hardly cause the precipitation of
carbon even under such a condition that the steam/carbon ratio is low, they have an advantage that
an excess amount of steam is not required and a reformed gas which is composed principally of

hydrogen can be produced at higher efficiency. However, these catalysts have a problem that they are expensive.

[0008] While ruthenium is relatively cheap, it is prone to be decreased in activity due to volatilization in the case where oxygen coexists at elevated temperatures such as those at which an autothermal reforming reaction is conducted.

[0009] Therefore, there has been demanded a cheap catalyst which hardly cause the carbon to precipitate even under such a condition that the steam/carbon ratio is low in an autothermal reforming reaction so as to be able to produce hydrogen at high efficiency and is excelled in heat resistance under the coexistence of oxygen, but such a catalysts has not been developed yet.

[0010] In view of the foregoing, an object of the present invention is to provide a catalyst having a sufficient activity and working life in an autothermal reforming process with maintaining the effect of suppressing the carbon to precipitate at a low steam/carbon ratio and comprising ruthenium which is relatively inexpensive.

BRIEF SUMMARY OF THE INVENTION

[0011] According to the present invention, there is provided an autothermal reforming catalyst comprising ruthenium supported on a support comprising 5 to 40 percent by mass of a cerium oxide or rare earth element oxide which is composed principally of a cerium oxide, 60 to 95 percent by mass of an aluminum oxide, and 0 to 10 percent by mass in terms of metal of one or more elements selected from the group consisting of an alkaline metal and an alkaline earth metal, the atomic ratio of cerium to ruthenium (Ce/Ru) being from 1 to 250.

[0012] According to the present invention, there is also provided the autothermal reforming catalyst characterized in that ruthenium in an amount of 0.1 to 3 percent by mass in terms of metal based on the weight of the catalyst is supported.

[0013] Furthermore, according to the present invention, there is provided a process of producing a fuel gas for a fuel cell wherein hydrocarbons and/or oxygen-containing hydrocarbons are converted to a reformed gas which is composed principally of hydrogen by an autothermal reforming reaction using the catalyst.

DETAILED DESCRIPTION OF THE INVENTION

[0014] First of all, the support used in the present invention is described.

[0015] The support used in the present invention characteristically comprises 5 to 40 percent by mass of a cerium oxide or rare earth element oxide which is composed principally of a cerium oxide, 60 to 95 percent by mass of an aluminum oxide, and 0 to 10 percent by mass in terms of metal of one or more elements selected from the group consisting of an alkaline metal and an alkaline earth metal.

[0016] No particular limitation is imposed on the cerium oxide used in the present invention. However, ceric oxide generally referred to as ceria is preferred.

[0017] No particular limitation is imposed on the method of preparing the cerium oxide which, therefore, may be prepared using cerium nitrate ($\text{Ce}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$, $\text{Ce}(\text{NO}_3)_4$), cerium chloride ($\text{CeCl}_3 \cdot n\text{H}_2\text{O}$), cerium hydroxide (CeOH_3 , $\text{CeOH}_4 \cdot \text{H}_2\text{O}$), cerium carbonate ($\text{Ce}_2(\text{CO}_3)_3 \cdot 8\text{H}_2\text{O}$, $\text{Ce}_2(\text{CO}_3)_3 \cdot 5\text{H}_2\text{O}$), cerium oxalate, cerium oxalate (IV) ammonium, or cerium chloride as the starting material in a conventional manner such as calcination in the air.

[0018] The rare earth element oxide which is composed principally of a cerium oxide may be prepared from the salts of a mixed rare earth element which is composed principally of cerium.

[0019] The rare earth metal which is composed principally of a cerium oxide contains a cerium oxide in an amount of generally 50 percent by mass or more, preferably 60 percent by mass or more, and more preferably 70 percent by mass or more.

[0020] Examples of the rare earth element oxide are oxides of each element such as scandium, yttrium, lanthanum, protheodymium, neodymium, promethium, samarium, europium, gadolinium, terbium, dysprosium, holmium, erbium, thulium, ytterbium, and lutetium. Among these, preferred are oxides of yttrium, lanthanum, and neodymium, and more preferred are oxides of lanthanum. No particular limitation is imposed on the form of their crystallinity, and they may, therefore, have any type of crystallinity form.

[0021] The aluminum oxide used in the present invention includes, other than alumina, double oxides of aluminum and other element such as silicon, copper, iron, and titanium. Typical examples of such double oxides are silica alumina and the like.

[0022] Particularly preferred for the aluminum oxide is alumina. No particular limitation is imposed on alumina which may, therefore, have any type of crystallinity form such as α , β , γ , η , θ , κ , and χ . Particularly preferred is γ -type alumina. There may also be used alumina hydrates such as boehmite, bialite, and gibbsite.

[0023] No particular limitation is imposed on silica alumina which may, therefore, be in any type of crystallinity form. Needless to mention, an aluminum oxide even containing a small amount of impurities can be used without hindrance.

[0024] Examples of the alkaline metal are lithium, sodium, potassium, rubidium, caesium, and francium. Preferred are potassium and caesium, and particularly preferred is caesium.

[0025] Examples of the alkaline earth metal are magnesium, calcium, strontium, barium, and radium. Preferred are magnesium, barium, and calcium, and particularly preferred is barium.

[0026] These elements may be used alone or in combination.

[0027] Upon preparation of the support for the catalyst, these elements may be used in the form of oxide, hydroxide, carbonate, nitrate, chloride, sulfate, or acetate.

[0028] When these elements are used as the support for the catalyst, they are generally used in the crystallinity form of oxide or carbonate.

[0029] The catalyst support used in the present invention contains a cerium oxide or rare earth element oxide which is composed principally of a cerium oxide in an amount of 5 to 40 percent by mass, and preferably 10 to 35 percent by mass. The rare earth metal oxide in an amount of less than 5 percent by mass is insufficient in the effects of suppressing carbon to precipitate, facilitating the activity, and enhancing the heat-resistance under coexistence of oxygen, while that in amount of more than 40 percent by mass reduces the catalyst surface, leading to insufficient catalyst activity.

[0030] The catalyst support used in the present invention contains the aluminum oxide in an amount of 60 to 95 percent by mass, and preferably 65 to 90 percent by mass. The aluminum oxide of less than 60 percent by mass reduces the catalyst surface, leading to insufficient catalyst activity, while that in excess of 95 percent by mass is insufficient in the effects of suppressing carbon to precipitate, facilitating the activity, and enhancing the heat-resistance under coexistence of oxygen.

[0031] The catalyst support used in the present invention contains the alkaline metal and/or alkaline earth metal in an amount of 0 to 10 percent by mass in terms of metal. The upper limit is 10 percent by mass, but is preferably 7 percent by mass or less. The alkaline metal and/or alkaline earth metal in excess of 10 percent by mass would invite the possibility that the catalyst activity is reduced. No particular limitation is imposed on the lower limit. Therefore, this component may not be present at all, but may be present in an amount of generally 0.5 percent by mass or more, and preferably 0.8 percent by mass or more.

[0032] It is preferred that the cerium oxide or rare earth metal element oxide which is composed principally of a cerium oxide, the aluminum oxide and the alkaline metal and/or alkaline earth metal be well-dispersed in the support.

[0033] No particular limitation is imposed on the method of producing the support used in the present invention, which may, therefore, be produced by any known suitable method at ease. For example, the support may be produced by impregnating an aluminum oxide with an water-soluble solution of a salt of cerium or a rare earth metal which is composed principally of cerium, followed by drying and calcination. Eligible salts for this method are water-soluble salts. Preferred salts are nitrates, chlorides, sulfates, and acetates. Particularly preferred are nitrates or organic acid salts which are easily decomposed by calcination and become oxides.

[0034] The calcination is generally effected in the air or an oxygen atmosphere. No particular limitation is imposed on the temperature as long as it is the decomposition temperature of the salt or higher. However, the temperature is generally 500 to 1,400°C, and preferably 700 to 1,200 °C.

[0035] Alternatively, the support may be prepared by coprecipitation, gel-kneading, and sol-gel methods.

[0036] In the case of preparing a support containing an alkaline metal and/or alkaline earth metal, no particular limitation is imposed on the method of adding the alkaline metal and/or alkaline earth metal into the support. For example, when a cerium oxide or rare earth element oxide which is composed principally of a cerium oxide is prepared, an aluminum oxide is prepared, or a support comprising a cerium oxide or rare earth element oxide which is composed principally of a cerium oxide and an aluminum oxide is prepared, a water-soluble solution of a nitrate, chloride or acetate of an alkaline metal and/or alkaline earth metal is impregnated into the precursor of the support, and then dried and calcined. Alternatively, after preparing a support comprising a cerium oxide or rare earth metal element oxide which is composed principally of a cerium oxide, and an aluminum oxide, a water-soluble solution of a nitrate, chloride or acetate of an alkaline metal and/or alkaline earth metal is impregnated into the support, and then dried and calcined.

[0037] Although the catalyst support can be obtained in such a manner, it is preferred that the catalyst support be calcined in the air or an oxygen atmosphere before ruthenium being supported on the support. The calcination temperature is generally 500 to 1,400 °C, and preferably 700 to 1,200 °C.

[0038] In order to enhance the mechanical strength of the catalyst support, a small amount of binder, such as silica and cement may be added thereto.

[0039] No particular limitation is imposed on the shape of the support used in the present invention. Therefore, any shape may be suitably selected depending on the use of the catalyst. For example, the support may take any type of shape such as pellet-, granular-, honey-comb-, and sponge-like shape.

[0040] The catalyst of the present invention can be obtained by supporting ruthenium on the above-described support. In the present invention, rhodium is used as an active metal. Ruthenium is supported in such an amount that the atomic ratio of cerium to ruthenium (Ce/Ru) is 1 to 250, preferably 2 to 100, and more preferably 3 to 50. The deviation of the atomic ratio from the range is not preferred because there is a possibility that sufficient catalyst activity may not be obtained.

[0041] The amount of ruthenium to be supported is 0.1 to 3.0 percent by mass, and preferably 0.5 to 2.0 percent by mass in terms of metal based on the total mass of the catalyst (total mass of the support and the active metal).

[0042] No particular limitation is imposed on the method of supporting ruthenium on the support. Any known method may be selected. For example, there may be employed impregnation, deposition, co-precipitation, kneading, ion-exchange, and pore-filling methods. Among these methods, particularly preferred is impregnation.

[0043] The starting materials of ruthenium differ depending on the method of supporting ruthenium and may be suitably selected. However, generally, a chloride or nitrate of ruthenium may be used. For example, in the case of employing impregnation, a solution (generally water-soluble solution) of a salt of ruthenium is prepared and impregnated into the support. The support is dried and if necessary calcined.

[0044] The calcination is generally effected in the air or a nitrogen atmosphere. No particular limitation is imposed on the calcination temperature as long as it is the decomposition temperature of the salt or higher. It is generally 200 to 800 °C, and preferably 300 to 600 °C.

[0045] It is preferred in the present invention to prepare the catalyst by subjecting the support supporting ruthenium to a reduction treatment under a reduction atmosphere, generally, a hydrogen atmosphere at a temperature of 400 to 1,000 °C, and preferably 500 to 700 °C.

[0046] In the present invention, the catalyst may further contain other noble metals such as rhodium, platinum, iridium, and palladium supported on the support as well to an extent not to hinder the achievement of purpose of the invention.

[0047] The surface area of the catalyst of the present invention is generally 5 to 200m²/g, and preferably 10 to 150m²/g, while the pore volume is generally 0.05 to 1.0cm³/g, and preferably 0.1 to 0.7cm³/g.

[0048] No particular limitation is imposed on the shape of the catalyst. Therefore, it may be selected suitably depending on the use of the catalyst. For example, the catalyst may take any suitable shape such as pellet-, granular-, honey-comb-, and sponge-like shape.

[0049] Next, a process of producing a fuel gas for a fuel cell is described which process comprises a step of converting hydrocarbons and/or oxygen-containing hydrocarbons to a reformed gas which is composed principally of hydrogen by an autothermal reforming reaction using the catalyst of the present invention.

[0050] In the case of using a gas as the feed stock in the autothermal reforming reaction, the gas preheated to a predetermined temperature is well-mixed with steam and air or oxygen, and then introduced into a reactor filled with the catalyst. In the case of using a liquid as the feed stock, the liquid is evaporated, well-mixed with steam and air or oxygen, and then introduced into a reactor filled with the catalyst. In the case where sulfur is contained in the feed stock, it is preferred that the feed stock be desulfurized before introducing into a reactor.

[0051] The reaction temperature is generally 200 to 800 °C, and preferably 300 to 600 °C at the inlet for the catalyst bed, and generally 500 to 1,000 °C, and preferably 600 to 800 °C at the exit for the catalyst bed.

[0052] The reaction pressure is generally atmospheric pressure to 5MPa, and preferably atmospheric pressure to 1MPa.

[0053] The steam to be introduced together with the feed stock is introduced in such an amount that the steam/carbon ratio (molar ratio) is 0.1 to 5.0, and preferably 0.5 to 3.0.

[0054] The oxygen to be introduced together with the feed stock is introduced in such an amount that the O₂/carbon ratio (molar ratio) is 0.1 to 0.5, and preferably 0.2 to 0.4.

[0055] In the present invention, the feed stock for producing a reformed gas which is composed principally of hydrogen may be hydrocarbons, oxygen-containing hydrocarbons, and mixtures

thereof. Specific examples are petroleum products such as methane, ethane, propane, butane, natural gas, LPG, manufactured gas, gasoline, naphtha, kerosene, and liquid fuels having a boiling point within the range of those thereof, alcohols such as methanol, ethanol, and propanol, and ethers such as dimethyl ether. The lesser the sulfur content, the better the hydrocarbons are. Particularly,
5 it is preferred that the sulfur content be 1 wtppm or less.

[0056] In the process of the present invention, the feed stock hydrocarbons such as hydrocarbons and/or oxygen-containing hydrocarbons are converted to a reformed gas which is composed principally of hydrogen in the presence of the catalyst by an autothermal reforming reaction. A fuel gas for a fuel cell is generally supplied to a fuel cell stack by a process which is the
10 combination of the desulfurization of the feed stock hydrocarbons prior to be subjected to an autothermal reforming treatment and the carbon monoxide conversion or carbon monoxide selective oxidation treatment of a reformed gas produced by an autothermal reforming. Alternatively, in place of the carbon monoxide conversion or carbon monoxide selective oxidation treatment after autothermal reforming, a fuel gas may be supplied to a fuel cell stack by a process which is the
15 combination of the desulfurization with a hydro-refining process using a hydrogen-permeable membrane.

[0057] The autothermal reforming catalyst of the present invention has an extremely high activity and long working life. However, in the case of continuing the use of the catalyst over a long period of time, if necessary, the catalyst is preferably subjected to a refresh treatment such as
20 reduction under a reduction atmosphere, generally, a hydrogen atmosphere at a temperature of 400 to 1,000 °C, and preferably 500 to 700 °C.

[0058] The autothermal reforming catalyst of the present invention is not decreased in activity even using ruthenium which has conventionally the tendency to be decreased in activity under an oxygen atmosphere at elevated temperatures, leading to a sufficient working life and can maintain
25 the effect of suppressing carbon to precipitate at a lower steam/carbon ratio. Furthermore, since the catalyst comprises ruthenium which is cheaper among the noble metals, it is advantageous in the industrial use.

EXAMPLES

[0059] The invention will be further described by way of the following examples which are
30 provided for illustrative purposes only.

EXAMPLE 1

[0060] (1) Preparation of Catalyst

[0061] γ -alumina powder with a specific surface of $190\text{m}^2/\text{g}$ was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a temperature of 120°C for 3 hours and then calcined in the air at a temperature of 800°C for 3 hours, thereby preparing a catalyst support.

[0062] The support was dipped into a water-soluble solution of ruthenium chloride, and then the water was evaporated therefrom. The support was dried at a temperature of 120°C for 3 hours.

After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500°C for 3 hours thereby obtaining Catalyst A. The chemical composition of Catalyst A is shown in Table 1.

[0063] (2) Autothermal Reforming Reaction

[0064] A reaction tube with an inner diameter of 9mm was filled with 1 cc of Catalyst A and then set in a tube-like electric oven. An autothermal reforming reaction was conducted by introducing desulfurized kerosene with the properties shown in Table 2 as the feed stock at an LHSV of 1.5h^{-1} into the reaction tube at a reaction temperature of 600°C , a steam/carbon ratio (molar ratio) of 3.0, and an oxygen/carbon ratio (molar ratio) of 0.33 and at atmospheric pressure for 20 hours.

[0065] The reaction gas was analyzed using gas chromatogram to determine the conversion rate by calculating the ratio of CO, CO₂, and CH₄ converted from the feed stock, i.e., kerosene, based on carbon. The results after 20 hours are shown in Table 1.

[0066] (3) Evaluation of Stability under an Oxygen Atmosphere

[0067] Catalyst A was calcined in the air at a temperature of 600°C for 5 hours thereby obtaining Catalyst A1. This calcination in the air corresponds to the accelerated oxidative deterioration conditions in an autothermal reforming reaction.

[0068] Thereafter, an autothermal reforming reaction was conducted using desulfurized kerosene as the feed stock and Catalyst A1 under the same conditions as those of the above (2) for

20 hours. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

EXAMPLE 2

[0069] (1) Preparation of Catalyst

5 [0070] γ -alumina powder with a specific surface of $190\text{m}^2/\text{g}$ was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a temperature of 120°C for 3 hours and then calcined in the air at a temperature of 800°C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of barium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of
10 120°C for 3 hours and calcined in the air at a temperature of 800°C for 3 hours.

[0071] The support was dipped into a water-soluble solution of ruthenium chloride, and then the water was evaporated therefrom. The support was dried at a temperature of 120°C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of
15 500°C for 3 hours thereby obtaining Catalyst B. The chemical composition of Catalyst B is shown in Table 1.

[0072] (2) Autothermal Reforming Reaction

[0073] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst B under the same conditions as those of Example 1. The
20 conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

[0074] (3) Evaluation of Stability under an Oxygen Atmosphere

[0075] Catalyst B was calcined in the air at a temperature of 600°C for 5 hours thereby obtaining Catalyst B1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst B1 under the same conditions as those of
25 Example 1. The conversion rate and the composition of the reformed gas 20 hours are shown in Table 1.

EXAMPLE 3

[0076] (1) Preparation of Catalyst

[0077] γ -alumina powder with a specific surface of $190\text{m}^2/\text{g}$ was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a temperature of 120°C for 3 hours and then calcined in the air at a temperature of 800°C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of magnesium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of 120°C for 3 hours and calcined in the air at a temperature of 800°C for 3 hours.

[0078] The support was dipped into a water-soluble solution of ruthenium chloride, and then the water was evaporated therefrom. The support was dried at a temperature of 120°C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500°C for 3 hours thereby obtaining Catalyst C. The chemical composition of Catalyst C is shown in Table 1.

[0079] (2) Autothermal Reforming Reaction

[0080] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst C under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

[0081] (3) Evaluation of Stability under an Oxygen Atmosphere

[0082] Catalyst C was calcined in the air at a temperature of 600°C for 5 hours thereby obtaining Catalyst C1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst C1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

EXAMPLE 4

[0083] (1) Preparation of Catalyst

[0084] γ -alumina powder with a specific surface of $190\text{m}^2/\text{g}$ was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a temperature of 120°C for 3 hours and then calcined in the air at a temperature of 800°C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of magnesium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of 120°C for 3 hours and calcined in the air at a temperature of 800°C for 3 hours.

[0085] The support was dipped into a water-soluble solution of ruthenium chloride, and then the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500 °C for 3 hours thereby obtaining Catalyst D. The chemical composition of Catalyst D is shown in Table 1.

[0086] (2) Autothermal Reforming Reaction

[0087] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst D under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

[0088] (3) Evaluation of Stability under an Oxygen Atmosphere

[0089] Catalyst D was calcined in the air at a temperature of 600 °C for 5 hours thereby obtaining Catalyst D1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst D1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

EXAMPLE 5

[0090] (1) Preparation of Catalyst

[0091] γ -alumina powder with a specific surface of 190m²/g was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a temperature of 120 °C for 3 hours and then calcined in the air at a temperature of 800 °C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of potassium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours and calcined in the air at a temperature of 800 °C for 3 hours.

[0092] The support was dipped into a water-soluble solution of ruthenium chloride, and then the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500 °C for 3 hours thereby obtaining Catalyst E. The chemical composition of Catalyst E is shown in Table 1.

[0093] (2) Autothermal Reforming Reaction

[0094] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst E under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

5 **[0095]** (3) Evaluation of Stability under an Oxygen Atmosphere

[0096] Catalyst E was calcined in the air at a temperature of 600 °C for 5 hours thereby obtaining Catalyst E1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst E1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown
10 in Table 1.

EXAMPLE 6

[0097] (1) Preparation of Catalyst

[0098] γ -alumina powder with a specific surface of 190m²/g was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a
15 temperature of 120 °C for 3 hours and then calcined in the air at a temperature of 800 °C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of potassium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours and calcined in the air at a temperature of 800 °C for 3 hours.

[0099] The support was dipped into a water-soluble solution of ruthenium chloride, and then the
20 water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500 °C for 3 hours thereby obtaining Catalyst F. The chemical composition of Catalyst F is shown in Table 1.

25 **[0100]** (2) Autothermal Reforming Reaction

[0101] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst F under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

[0102] (3) Evaluation of Stability under an Oxygen Atmosphere

[0103] Catalyst F was calcined in the air at a temperature of 600 °C for 5 hours thereby obtaining Catalyst F1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst F1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

EXAMPLE 7

[0104] (1) Preparation of Catalyst

[0105] γ -alumina powder with a specific surface of 190m²/g was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a temperature of 120 °C for 3 hours and then calcined in the air at a temperature of 800 °C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of caesium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours and calcined in the air at a temperature of 800 °C for 3 hours.

[0106] The support was dipped into a water-soluble solution of ruthenium chloride, and then the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500 °C for 3 hours thereby obtaining Catalyst G. The chemical composition of Catalyst G is shown in Table 1.

[0107] (2) Autothermal Reforming Reaction

[0108] (3) Evaluation of Stability under an Oxygen Atmosphere

[0109] Catalyst G was calcined in the air at a temperature of 600 °C for 5 hours thereby obtaining Catalyst G1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst G1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

EXAMPLE 8

[0110] (1) Preparation of Catalyst

[0111] Silica-alumina powder with a specific surface of 180m²/g was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a

temperature of 120 °C for 3 hours and then calcined in the air at a temperature of 800 °C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of caesium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours and calcined in the air at a temperature of 800 °C for 3 hours.

5 **[0112]** The support was dipped into a water-soluble solution of ruthenium chloride, and then the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500 °C for 3 hours thereby obtaining Catalyst H. The chemical composition of Catalyst H is shown
10 in Table 1.

[0113] (2) Autothermal Reforming Reaction

[0114] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst H under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

15 **[0115]** (3) Evaluation of Stability under an Oxygen Atmosphere

[0116] Catalyst H was calcined in the air at a temperature of 600 °C for 5 hours thereby obtaining Catalyst H1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst H1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown
20 in Table 1.

EXAMPLE 9

[0117] (1) Autothermal Reforming Reaction

[0118] An autothermal reforming reaction was conducted for 20 hours using desulfurized light naphtha with the properties shown in Table 2 as the feed stock and Catalyst H in the same manner as
25 that of Example 1. The reaction was conducted at a temperature of 600 °C, a steam/carbon ratio (molar ratio) of 3.0, an oxygen/carbon ratio (molar ratio) of 0.33, atmospheric pressure, and an LHSV of 5h-1. The properties of the feed stock are shown in Table 1. The conversion rate and the composition of the reformed gas after 20 hours are also shown in Table 1.

[0119] (2) Evaluation of Stability under an Oxygen Atmosphere

[0120] An autothermal reforming reaction was conducted for 20 hours using desulfurized light naphtha as the feed stock and Catalyst H1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are also shown in Table 1.

EXAMPLE 10

5 [0121] (1) Autothermal Reforming Reaction

[0122] An autothermal reforming reaction was conducted for 20 hours using propane with a purity of 99.5% or higher and the properties shown in Table 2 as the feed stock and Catalyst H in the same manner as that of Example 1. The reaction was conducted at a temperature of 600 °C, a steam/carbon ratio (molar ratio) of 3.0, an oxygen/carbon ratio (molar ratio) of 0.33, atmospheric
10 pressure, and an LHSV of 10h⁻¹. The conversion rate and the composition of the reformed gas after 20 hours are also shown in Table 1.

[0123] (2) Evaluation of Stability under an Oxygen Atmosphere

[0124] An autothermal reforming reaction was conducted for 20 hours using propane as the feed stock and Catalyst H1 under the same conditions as those of Example 1. The conversion rate and
15 the composition of the reformed gas after 20 hours are also shown in Table 1.

COMPARATIVE EXAMPLE 1

[0125] (1) Preparation of Catalyst

[0126] γ -alumina powder with a specific surface of 190m²/g was calcined in the air at a temperature of 800 °C for 3 hours thereby obtaining a support. The support was then dipped into a
20 water-soluble solution of ruthenium chloride, and the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500 °C for 3 hours thereby obtaining Catalyst I. The chemical composition of Catalyst I is shown in Table 1.

25 [0127] (2) Autothermal Reforming Reaction

[0128] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst I under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

[0129] (3) Evaluation of Stability under an Oxygen Atmosphere

[0130] Catalyst I was calcined in the air at a temperature of 600 °C for 5 hours thereby obtaining Catalyst II. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst II under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are also shown in Table 1.

5

COMPARATIVE EXAMPLE 2

[0131] (1) Preparation of Catalyst

[0132] γ -alumina powder with a specific surface of 190m²/g was dipped into a water-soluble solution of cerium nitrate, and the water is evaporated therefrom. The powder was dried at a temperature of 120 °C for 3 hours and then calcined in the air at a temperature of 800 °C for 3 hours, thereby preparing a catalyst support. The support was dipped into a water-soluble solution of caesium nitrate, and the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours and calcined at a temperature of 800 °C for 3 hours.

[0133] The support was dipped into a water-soluble solution of ruthenium chloride, and the water was evaporated therefrom. The support was dried at a temperature of 120 °C for 3 hours. After the support was pressed, it was ground and sifted, thereby obtaining a granulated catalyst with a size of about 1 to 2mm. The catalyst was reduced under a hydrogen circulation at a temperature of 500 °C for 3 hours thereby obtaining Catalyst J. The chemical composition of Catalyst J is shown in Table 1.

[0134] (2) Autothermal Reforming Reaction

[0135] An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst J under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

[0136] (3) Evaluation of Stability under an Oxygen Atmosphere

[0137] Catalyst J was calcined in the air at a temperature of 600 °C for 5 hours thereby obtaining Catalyst J1. An autothermal reforming reaction was conducted for 20 hours using desulfurized kerosene as the feed stock and Catalyst J1 under the same conditions as those of Example 1. The conversion rate and the composition of the reformed gas after 20 hours are shown in Table 1.

[0138] As apparent from Table 1, Catalysts A to H are extremely low in activity reduction even though they are calcined in the air assuming oxidation deterioration at elevated temperature in an autothermal reforming reaction, and is excellent in anti-oxidation properties.

30

TABLE 1

	Inventive Examples											
	1		2		3		4		5		6	
Feed Stock	Desulfurized Kerosene		Desulfurized Kerosene		Desulfurized Kerosene		Desulfurized Kerosene		Desulfurized Kerosene		Desulfurized Kerosene	
Catalyst	A	Al	B	Bl	C	Cl	D	Dl	E	El	F	Fl
Catalyst Composition (mass%)												
SiO ₂ ·Al ₂ O ₃	-	-	-	-	-	-	-	-	-	-	-	-
Al ₂ O ₃	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance
CeO ₂	20	20	20	20	20	20	10	10	10	10	10	10
Ba	-	-	5	5	-	-	-	-	-	-	-	-
Mg	-	-	-	-	5	5	5	5	-	-	-	-
K	-	-	-	-	-	-	-	-	5	5	-	-
Cs	-	-	-	-	-	-	-	-	-	-	5	5
Ru	1	1	1	1	1	1	2	2	2	2	2	2
Conversion Rate (%)	100	100	100	100	100	100	100	100	100	100	100	100
Carbon Precipitation Amount (mass%)	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1
Composition of Reformed Gas (volume%, dry basis)												
H ₂	47.5	47.2	48.1	47.9	48.0	48.0	47.8	47.0	47.5	47.2	48.0	47.7
CO	7.0	6.8	7.1	7.0	6.9	7.0	7.5	7.0	7.1	6.7	7.0	6.9
CO ₂	15.1	15.3	15.0	15.2	15.1	15.5	15.0	15.1	15.3	15.4	15.2	15.3
CH ₄	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
O ₂	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
N ₂	30.0	30.3	29.4	29.5	29.7	29.0	29.3	30.5	29.7	30.3	29.4	29.7

Table 1 cont'd

	Inventive Examples								Comparative Examples			
	7		8		9		10		1		2	
Feed Stock	Desulfurized Kerosene		Desulfurized Kerosene		Desulfurized Light Naptha		Propane		Desulfurized Kerosene		Desulfurized Kerosene	
Catalyst	G	G1	H	H1	H	H1	H	H1	I	II	J	J1
Catalyst Composition (mass%)												
5 $\text{SD}_2 \cdot \text{Al}_2\text{O}_3$	-	-	balance	balance	balance	balance	balance	balance	-	-	-	-
Al_2O_3	balance	balance	-	-	-	-	-	-	99	99	balance	balance
CeO_2	10	10	10	10	10	10	10	10	-	-	1	1
Ba	-	-	-	-	-	-	-	-	-	-	-	-
Mg	-	-	-	-	-	-	-	-	-	-	-	-
K	-	-	-	-	-	-	-	-	-	-	-	-
Cs	5	5	5	5	5	5	5	5	-	-	5	5
Ru	1	1	1	1	1	1	1	1	1	1	1	1
Conversion Rate (%)	100	100	100	100	100	100	100	100	85	57	88	65
10 Carbon Precipitation Amount (mass%)	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	<0.1	1	4	1	3
Composition of Reformed Gas (volume%, dry basis)												
H_2	47.3	47.0	47.5	46.9	46.0	45.9	45.9	45.8	46.0	24.8	46.2	35.0
CO	7.0	6.8	6.9	6.6	7.0	7.0	7.1	7.0	6.0	4.1	6.3	5.5
CO_2	15.0	15.5	15.2	15.3	14.2	14.3	13.9	14.0	16.0	18.6	15.5	17.0
CH_4	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.4	0.9	0.4	0.5
O_2	0.2	0.2	0.2	0.2	0.1	0.1	0.1	0.1	0.3	0.4	0.2	0.3
N_2	30.3	30.3	30.0	30.8	32.5	32.5	32.8	32.9	31.3	51.2	31.4	41.7

TABLE 2

Feed Stock	Desulfurized Kerosene	Desulfurized Light Naptha	Propane
Density g/cm^3 (@15°C)	0.7943	0.6407	0.5080
Distillation Properties			
Initial Point °C	154.0	25.5	
Running Point at 10vol.% °C	173.0	32.5	
Running Point at 50vol.% °C	199.0	41.5	
Running Point at 90vol.% °C	239.0	60.0	
Running Point at 95vol.% °C	248.5	66.0	
End Point °C	262.5	71.5	
Sulfur Contents mass ppm	<1	<1	<1
Composition			
Paraffins volume ppm	84.6	99.9	
Olefins volume ppm	0.0	0.0	
Aromatics volume ppm	15.4	0.1	

[00100] It will be appreciated by those skilled in the art that changes could be made to the embodiments described above without departing from the broad inventive concept thereof. It is understood, therefore, that this invention is not limited to the particular embodiments disclosed, but it is intended to cover modifications within the spirit and scope of the present invention as defined
5 by the appended claims.